



FLEXOGRAFIA

Adhesivo Termo-sellable flexo base agua

PX-653-788

Application

Development PX-653-78 is a clear, heat sealable, water based adhesive for turn laminations. Activation temperature of 120 F to 140 F. Yields superior mileage, tack range. non-warping. non—skinning for excellent machining and clean.

The product is suitable for Flexo and roll coating. Excellent pan stability with very little foaming and clean up required. General purpose adhesive for coated, high bulk and offset. Good water resistance, flexibility and adhesion.



Physical Properties

- **APPEARANCE:** White liquid, dries clear.
- **VISCOSITY:** 900-1100 CPS (Brookfield, 20 rpm. spindle 2. 77°F)
- **SOLIDS:** 50+/- 2%
- **PH:** 7.0-0.0
- **CLEAN UP:** Warm, soapy water while still wet; final clean up with solvent, e.g. acetone, ethyl acetate. isopropanol.
- **STORAGE CONDITIONS:** Store below 00°F. Keep from freezing and excessive heat and cold. If very cold. product should he warmed slowly. Low temperatures will thicken product: high temperatures will thin product. If frozen. product is unusable.

